

13441US

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Applicants: Zuber *et al.* Examiner: To be assigned
Serial No.: 10/668,559 Group Art Unit: To be assigned
Filed: September 22, 2003
For: "Catalyst-coated ionomer membrane with protective film layer and
membrane-electrode-assembly made thereof"

Customer No.: 23719

Kalow & Springut LLP
488 Madison Avenue, 19th Floor
New York, New York 10022

April 2, 2004

Commissioner for Patents
P.O. Box 1450
Alexandria, VA 22313-1450


TRANSMITTAL OF PRIORITY DOCUMENT

Sir:

Enclosed is a copy of the certified priority document for the above-identified application.
If any fee is due please charge Deposit Account No. 11-0171 for such sum accordingly.

If there are any questions regarding this matter, the Examiner is respectfully invited to
contact the Applicants' attorney at the telephone number given below. Thank you for your time
and attention to this matter.

Respectfully submitted,




Scott D. Locke, Esq.
Registration No.: 44,877
Attorney for Applicant


(212) 813-1600

Certificate of Mailing Under 37 C.F.R. 1.8


I hereby certify that this correspondence is being deposited on the date shown below with the United States Postal
Service as first class mail with sufficient postage in an envelope addressed to: Commissioner for Patents, P.O. Box
1450, Alexandria, VA 22313-1450.



(Signature)



(Printed Name of Person Signing
Certificate)



(Date)



THIS PAGE BLANK (USPTO)



**Europäisches
Patentamt**

**European
Patent Office**

**Office européen
des brevets**

Bescheinigung

Certificate

Attestation

Die angehefteten Unterlagen stimmen mit der ursprünglich eingereichten Fassung der auf dem nächsten Blatt bezeichneten europäischen Patentanmeldung überein.

The attached documents are exact copies of the European patent application described on the following page, as originally filed.

Les documents fixés à cette attestation sont conformes à la version initialement déposée de la demande de brevet européen spécifiée à la page suivante.

Patentanmeldung Nr. Patent application No. Demande de brevet n°

02021990.3

Der Präsident des Europäischen Patentamts;
Im Auftrag

For the President of the European Patent Office

Le Président de l'Office européen des brevets
p.o.

R C van Dijk

THIS PAGE BLANK



Anmeldung Nr:
Application no.: 02021990.3
Demande no:

Anmeldetag:
Date of filing: 30.09.02
Date de dépôt:

Anmelder/Applicant(s)/Demandeur(s):

OMG AG & Co. KG
Rodenbacher Chaussee 4
63457 Hanau-Wolfgang
ALLEMAGNE

Bezeichnung der Erfindung/Title of the invention/Titre de l'invention:
(Falls die Bezeichnung der Erfindung nicht angegeben ist, siehe Beschreibung.
If no title is shown please refer to the description.
Si aucun titre n'est indiqué se referer à la description.)

Catalyst-coated ionomer membrane with protective film layer and membrane-electrode-assembly made thereof

In Anspruch genommene Priorität(en) / Priority(ies) claimed /Priorité(s)
revendiquée(s)

Staat/Tag/Aktenzeichen/State/Date/File no./Pays/Date/Numéro de dépôt:

Internationale Patentklassifikation/International Patent Classification/
Classification internationale des brevets:

H01M8/00

Am Anmeldetag benannte Vertragsstaaten/Contracting states designated at date of
filing/Etats contractants désignées lors du dépôt:

AT BE BG CH CY CZ DE DK EE ES FI FR GB GR IE IT LI LU MC NL PT SE SK TR

THIS PAGE BLANK

**Catalyst-coated ionomer membrane with protective film layer
and membrane-electrode-assembly made thereof**

Field of the Invention

The present invention relates to the field of electrochemical cells and fuel cells.

5 Background

Fuel cells convert a fuel and an oxidizing agent into electricity, heat and water at two spatially separated electrodes. Typically in fuel cells, hydrogen or a hydrogen-rich gas is used as the fuel, and oxygen or air is used as the oxidizing agent.

10 The energy conversion process in fuel cells is distinguished by particularly high efficiency. For this reason, fuel cells are gaining increasing importance for mobile, stationary and portable applications.

15 The polymer electrolyte membrane fuel cell (PEMFC) and the direct methanol fuel cell (DMFC, a variation of the PEMFC, powered directly by methanol instead of hydrogen) are two common types of fuel cells that are used as energy converting devices. They are attractive choices because typically, they have compact designs, desirable power densities and high efficiencies.

20 The technology of fuel cells is well known to persons skilled in the art and is broadly described in the literature, see for example, K. Kordesch and G. Simader, "Fuel Cells and its Applications," VCH Verlag Chemie, Weinheim (Germany) 1996. Nonetheless, in order to aid in the understanding of the present invention, in the following section, certain technical terms and phrases that are used in the present disclosure are described in greater detail:

25 A "catalyst-coated membrane" (hereinafter abbreviated "CCM") consists of a polymer electrolyte membrane that is provided on both sides with a catalytically active layer. One of the layers takes the form of an anode for the oxidation of hydrogen and the other layer takes the form of a cathode for the reduction of oxygen. Because the CCM consists of three layers (anode catalyst layer, ionomer membrane and cathode catalyst layer), it is often referred to as a "three-layer MEA." As outlined in this disclosure, a

CCM may also contain one or more film layers for better protection, handling and sealing of the product.

“Gas diffusion layers” (“GDLs”), sometimes referred to as gas diffusion substrates or backings, are placed onto the anode and cathode layers of the CCM in order to bring the gaseous reaction media (*e.g.*, hydrogen and air) to the catalytically active layers and, at the same time, to establish an electrical contact. GDLs usually consist of carbon-based substrates, such as carbon fiber paper or woven carbon fabric, which are highly porous and provide the reaction gases with good access to the electrodes. Furthermore, they are hydrophobic and permit removal of the product water from the fuel cell. Additionally, GDLs can be coated with a microlayer in order to improve the contact to the membrane. They can also be tailored specifically into anode-type GDLs or cathode-type GDLs, depending on into which side they are built in a given MEA. Furthermore, they can be coated with a catalyst layer and subsequently laminated to the ionomer membrane. These types of catalyst-coated GDLs are frequently referred to as “catalyst-coated backings” (abbreviated “CCBs”) or gas diffusion electrodes (“GDEs”).

A “membrane-electrode-assembly” (“five-layer MEA”) is the central component in a polymer-electrolyte-membrane (PEM) fuel cell and consists of five layers: the anode GDL; the anode catalyst layer; the ionomer membrane; the cathode catalyst layer; and the cathode GDL. A MEA can be manufactured by combining a CCM with two GDLs (on the anode and the cathode side) or, alternatively, by combining an ionomer membrane with two catalyst-coated backings (CCBs) at the anode and the cathode sides. In both cases, a five-layer MEA product is obtained. When the CCM contains one or more protective film layers integrated in the laminated assembly, the five-layer MEA in turn contains the protective film layer or layers as well.

The anode and cathode catalyst layers are comprised of electrocatalysts that catalyze the respective reactions (*e.g.*, oxidation of hydrogen at the anode and reduction of oxygen at the cathode). Preferably, the metals of the platinum group of the periodic table are used as the catalytically active components, and for the most part, supported catalysts are used in which the catalytically active platinum group metals have been fixed in nano-sized particle form to the surface of a conductive support material. By

way of example, carbon blacks with particle sizes of 10 to 100 nm and high electrical conductivity have proven to be suitable as support materials. In these applications, the average particle size of the platinum group metal is typically between about 1 and 10 nm.

- 5 The "polymer electrolyte membrane" consists of proton-conducting polymer materials. These materials are also referred to below as ionomer membranes. In ionomer membranes, tetrafluoroethylene-fluorovinyl-ether copolymer with sulfonic acid groups is preferably used. This material is marketed, for example, by E.I. DuPont under the trade name Nafion®. However, other, especially fluorine-free, ionomer materials such as sulfonated polyether ketones or aryl ketones or acid-doped polybenzimidazoles may also be used. Examples of materials that are suitable as ionomer materials are described by O. Savadogo in "Journal of New Materials for Electrochemical Systems" I, 47-66 (1998). For application in fuel cells, these membranes generally have a thickness between 10 and 200 μm .
- 10
- 15 Within fuels cells several membrane-electrode-assemblies and bipolar plates are stacked in series to obtain the desired voltage output. As persons skilled in the art are aware, in fuel cell stack technology, sealing of components is an important issue. Generally, it is necessary to achieve a gas-tight sealing of these components (predominantly CCMs, MEAs and bipolar plates) against leakage to the environment and
- 20 against intermixing of the reactants (hydrogen and oxygen/air). This gas-tight seal is essential for the safety of a PEMFC stack. (Lack of safety is a serious obstacle for the widespread introduction of fuel cell technology.) Thus, the quality and endurance of the seals and the materials used for them are of primary importance.

For different stack architectures and operating conditions (such as pressure, temperature, fuel gases and lifetime required) different sealing concepts and technologies must be applied and developed. Furthermore, an appropriate sealing concept for CCMs and MEAs should also take into account an improvement for better protection and better handling of these products. Better handling and processing is particularly important in view of a large scale continuous production of CCMs and MEAs.

25

- 30 Various concepts and technologies for sealing of MEAs and CCMs are described in the prior art.

In U.S. Patent No. 3,134,697, a sealing function is conventionally achieved by using pre-cut frames of a polymer material and placing these frames around the electrodes of the fuel cell between the membrane and the bipolar plates of the cell. However, this concept suffers from the high efforts needed for exact handling and positioning of the cell, membrane-electrode-assembly and gasket frames. Thus, there is no close contact between membrane and sealing.

EP 690 519 addresses the stabilization of the membrane in the inactive sealing region. It relates to an assembly consisting of at least one seal layer in a solid polymer ion exchange layer, wherein the seal layer or layers cover essentially only the region of the ion exchange layer that is to be sealed. According to this application, the sealing layer is made of polytetrafluoroethylene (PTFE) film having one surface coated and partially impregnated with the ionomer material.

A similar concept is pursued in WO 00/74160. This document describes a membrane electrode unit for fuel cells. There the membrane electrode unit comprises a reinforcing frame that is situated on the periphery and in the area of openings that are placed in the active portion of the membrane electrode unit and provided for guiding material or for installation. A reinforcing frame is formed by a hot melt type adhesive layer that is applied on both sides and is formed by at least one rigid plate.

All of these concepts described in the aforementioned references are based on sealing frames or layers that cover the peripheral membrane rim of the CCM/MEA and only stabilize this peripheral rim. However, depending on fuel cell operating parameters, frequently failures in the membrane material may occur at the interface between the active area and the sealing layers. Therefore, sufficient overlap is needed between the sealing/gasket layer, the active electrode layer and the ionomer membrane.

WO 00/74161 relates to a membrane-electrode-assembly provided for fuel cells or the like that comprises an ionomer membrane that is coated on both sides with electrodes. The sealing edge, which is configured on the outer periphery, is comprised of a hot melt adhesive whose hydrocarbon skeleton carries, at regular intervals, ionic or strong polar groups that enter into a surface interaction with the ionic groups of the membrane material and thus provides for good adhesive effect of the hot melt type adhesive to the polymer electrolyte membrane. The thermoplastic sealing made of hot melt

type adhesive extends on both sides over the edge section of the membrane. Unfortunately, associated with this method are high production costs, as well as costs for the application form of the hot-melt adhesive. Furthermore, its long-term stability is not proven; various components (such as hardeners, defoamers and other additives) may
5 be leached out during operation and may cause deterioration of the MEA.

WO 00/10216 describes a membrane electrode gasket assembly ("MEGA") having a gasket and a sub-gasket to seal the MEA and to protect it from possible edge failures. The gasket material typically consists of expanded polytetrafluoroethylene (e-PTFE), soaked with a solution of ionomer for better adhesion. The sub-gasket is disposed
10 over a peripheral portion of an electrode, which is applied to a central portion of an ionomer membrane. In the examples given in WO 00/10216, a simultaneous overlapping of the sub-gasket with the electrode portion and the non-coated ionomer membrane portion is not disclosed.

A different concept is suggested in U.S. Patent No. 5,176,966. According to that patent, seals are formed by impregnating the layers of porous electroconductive sheet
15 material of the membrane-electrode-assembly with a sealant material that generally circumscribes the fluid passage openings and the electrochemical active portions of the assembly.

Another disclosure, WO 98/33225, is directed to a sealing that penetrates an edge of
20 at least one gas diffusion electrode (GDE) whereby the pores of the electrodes are filled. In that disclosure, the sealing is bonded to the membrane where the sealing penetrates the electrodes and comes into contact with the membrane and is also bonded to the peripheral face of the membrane. Both surfaces of the membrane are essentially completely covered by the electrodes.

25 The latter two concepts, which are based on impregnation of gas diffusion electrodes (GDEs) with a sealant material, suffer from the complexity of the impregnation process. Even small deviations of the process parameters strongly affect quality of sealing and the smoothness of the contact surface of the sealed area. Consequently, it is very difficult to obtain gas-tight seals.

In light of the shortcomings of the prior art, the present invention is directed to an improved catalyst-coated membrane that avoids the described disadvantages of the state of the art. In particular, the present invention provides a catalyst-coated membrane embracing one or more protective film layers that offers the following advantages: (i) improved mechanical stability; (ii) improved protection against membrane damage; and (iii) improved handling properties in cell/stack assembly. The present invention also provides an improved membrane-electrode-assembly (MEA) that offers the above-mentioned advantages. Finally, a process for manufacture of these improved products is outlined.

10 Summary of the Invention

The present invention relates to the field of electrochemical cells and fuel cells, more specifically to polymer-electrolyte-membrane fuel cells (PEMFC) and direct methanol fuel cells (DMFC), and describes catalyst-coated ionomer membranes ("CCMs") embracing one or more film layers for protection, sealing and handling purposes. The catalyst-coated membranes may, for example, be used as components for membrane-electrode-assemblies (MEAs) in low temperature fuel cell stacks.

According to one embodiment, the present invention provides a catalyst-coated membrane that comprises:

- a) an ionomer membrane, wherein said ionomer membrane comprises two surfaces and each of said two surfaces is comprised of:
 - (i) an active area, wherein said active area is coated with a catalyst layer; and
 - (ii) a passive area; and
- b) at least one layer of protective film attached to each of the two surfaces of said catalyst coated membrane, wherein said at least one layer of protective film overlaps the active area and the passive area.

According to a second embodiment, the present invention provides a membrane-electrode-assembly comprising:

- (a) an ionomer membrane, wherein said ionomer membrane comprises two surfaces and each of said two surfaces is comprised of:

- (i) an active area, wherein said active area is coated with a catalyst layer, and
- (ii) a passive area; and
- b) at least one gas diffusion layer, wherein said at least one gas diffusion layer covers the active area of said catalyst-coated membrane; and
- c) at least one layer of protective film, wherein said at least one layer of protective film contacts the active area, the passive area and the gas diffusion layer to form:
 - (i) an overlapped region of the active area,
 - (ii) an overlapped region of the passive area, and
 - (iii) an overlapped region of the gas diffusion layer.

In both of these embodiments, the passive area is the area of the ionomer membrane that has not been coated with a catalyst layer, and preferably, it forms a perimeter around the active area.

- These CCM and MEA are preferably manufactured under pressure and heat for a period of 0.1 to 15 minutes. More preferably, the pressure is in the range of 10 to 100 bar and the temperature is in the range of 20 to 200°C.

Brief Description of the Figures

Figure 1 is a representation of a catalyst-coated membrane (CCM) according to a first embodiment of the present invention.

Figure 2 is a representation of a cross-section of a membrane-electrode-assembly (MEA) with protective film layers according to a second embodiment of the present invention.

Detailed Description of the Invention

- The present invention is directed to catalyst-coated membranes and membrane-electrode-assemblies that contain ionomer membranes that have both an active area, which has a catalyst layer, and a passive area. Both of these areas are at least in part

coated with a protective film. In the MEA, the active area may be coated with a gas diffusion layer.

The present disclosure is not intended to be a treatise on catalyst-coated membranes or membrane-electrode-assemblies. Readers are referred to appropriate available texts
5 for background on these subjects.

According to the present invention, the catalyst coated membrane preferably comprises an ionomer membrane that itself is comprised of a substance selected from the group consisting of perfluorinated sulfonic acid polymers, acid-doped polybenzimidazoles, acid-group-modified polyetherketones, ionically conductive organic/inorganic
10 materials and composite reinforced materials.

Catalyst coated membranes typically have two sides that contain catalytically active materials. Each of these sides is referred to herein as a "surface." On each of the two surfaces of the ionomer membrane, there is both an active area and a passive area. The active area, which corresponds to the electrode area is coated with a catalyst
15 layer. The passive area, which is not coated, preferably forms a peripheral rim around the active area.

A protective film layer covers at least a portion of both the active area and the passive area. The protective film layer embraces the CCM on both sides of the membrane, and has two main features. First, it overlaps the active area in a certain region sufficient for prevention of membrane damage. Second, it overlaps a significant region of
20 the passive, non-coated area of the CCM. The region of the active area overlapped by the protective film layer is preferably in the range of 0.5 to 20 % of the total active area, and more preferably in the range of from 3 to 10 %. On the other hand, the region of the passive membrane area overlapped by the protective film layer is preferably
25 in the range of 80 to 150 %, more preferably in the range of 80 to 100% and most preferred equal to 100 %, of the total non-coated membrane area. Overlapping of more than 100 % in the context of the present invention means that the protective film would extend over the periphery of the ionomer membrane.

Preferably, the film comprises an organic polymer material with a thickness in the
30 range of 10 to 150 μm . More preferably, the organic polymer material is a thermo-

plastic, duroplastic or elastomeric polymer comprised of a polymer selected from the group consisting of polytetrafluoroethylene, PVDF, polyester, polyamide, copolyamide, polyamide elastomers, polyimide, polyurethane, polyurethane elastomers, silicones, silicon rubbers and silicon based elastomers.

- 5 Generally, one or more film layers can be applied on the front and/or on the back surface of the catalyst-coated membrane. During lamination, the protective film softens and can penetrate the electrode layer.

In a preferred embodiment, the protective film layers are applied as frames on both sides of the ionomer membrane. However, other patterns and dimensions are possible.

- 10 The protective film layer or layers may be punched or perforated as needed for certain bipolar plate and PEM stack architectures. Additional layers of protective films, such as gaskets or sealant materials may be added afterwards.

The present invention has two major embodiments, which are demonstrated in figures 1 and 2, and that may be incorporated into and operated in fuel cells such as PEMFCs
15 and DMFCs.

Figure 1 shows a schematic drawing (cross section) of a catalyst-coated membrane (CCM) according to the first embodiment of the present invention. According to this embodiment, the ionomer membrane (1) is coated on both sides with an electrode layer (2) forming the active area of the catalyst-coated membrane. Two frames of protective film layer (3) are applied on both sides to the passive area of the membrane (1)
20 in such a way that the film layers overlap with the electrode layers in an area region (4), and, simultaneously, with the passive, non-coated area of the ionomer membrane in an area region (5). On each side of the membrane, the region covered or overlapped by the protective film layer is in the range of 0.5 to 20 % of the total active area of the
25 membrane.

The protective film may be made of a polymer that is more rigid than the ionomer membrane. The thickness of the protective film is preferably in the range of 10 μm to 150 μm (more preferably in the range of 80 to 120 μm), which enables it to constitute a protection for the ionomer membrane against pressure, impact, wear, heat, drying

out, etc. In certain cases the thickness of the protective film may exceed 150 μm – especially when the protective film has also to function as a compressible sealing.

The protective film layer is tightly fixed onto the membrane. It can be pre-shaped and heat-laminated or attached by an adhesive onto the membrane. It can also be formed
5 by coating (by paste application, printing process, etc.) the non-coated membrane area with an appropriate polymer paste or polymer emulsion.

The respective materials should be stable and resistant to the operating conditions of a PEM fuel cell. Furthermore, the materials should have high endurance and lifetime, as well as high purity in respect to trace contaminants, residual volatile components and
10 other inorganic or organic materials that could be leached out during operation of the fuel cell.

Figure 2 depicts a cross-section of a membrane-electrode-assembly (MEA) with protective film layers according to the second embodiment of the present invention. In this second embodiment, the active area of the CCM according to embodiment 1 is
15 covered by gas diffusion layers (GDLs) in such a way, that the gas diffusion layers contact, overlap and/or penetrate the protective film layer applied to the CCM. Again, the ionomer membrane (1) is coated with an electrode layer (2) on both sides. The area of the active layer (2) (the “active area”) is smaller than the total area of the ionomer membrane, which results in a peripheral rim of uncoated ionomer material
20 (which is the passive non-coated area) around the central active area of the CCM. As already described in embodiment 1, two frames of protective film layers (3) are attached on both sides to the passive area of the membrane (1) in such a way that the film layers overlap with the electrode layers in an area region (4), and, simultaneously, with the passive, non-coated area of the ionomer membrane in an area region
25 (5). On each side of the CCM, the region covered/overlapped by the protective film layer is in the range of 0.5 to 20 % of the total active area. Both surfaces of the CCM are additionally covered by gas diffusion layers (6). These two gas diffusion layers (GDLs) overlap/contact the protective film layer disposed over part of the active area at both sides of the membrane (overlapping region 7).

30 In a preferred embodiment, the dimensions of the GDL and that of the active area are identical. In this case, the region of the active area of the CCM overlapped by the pro-

5 protective film and the region of the GDL in contact with the protective film are identical. However, other embodiments, involving GDLs with bigger or smaller dimensions compared to the active CCM area, are possible. Thus, the region of the GDL contacted by the layer of protective film can be in the range of 0.5 to 50 % of the total area of the gas diffusion layer.

It is furthermore feasible, to provide the protective film in a first step as a liquid, to press the GDL into the liquid film and to cure the film providing a solid protective film penetrating the GDL.

10 Commercially available GDLs, as well as other suitable materials can be used for the formation of the membrane-electrode-assembly (MEA) according to this invention. As base materials for GDLs, woven carbon cloth, non-woven carbon fiber layers or carbon fiber papers can be used. Typical GDL base materials include Toray TGP-H-060 and Textron AvCarb 1071 HCB supplied by Textron Inc. The gas diffusion layers may or may not be treated to be hydrophobic. Additionally, they may comprise additional carbon black microlayers and catalyst layers, if necessary.

Bonding of the GDLs to the CCM can be conducted by application of pressure and heat. Appropriate bonding or laminating conditions have to be adopted to the mechanical stability of the individual base material of the GDLs.

Examples

20 The following examples describe the scope of the invention in more detail. These examples are presented to aid in an understanding of the present invention and are not intended, and should not be construed, to limit the invention in any way.

Example 1:

25 The catalyst-coated membrane used in this example was manufactured according to U.S. Patent No. 6,309,772, example 3, ink A. A 40 wt.% Pt/Vulcan XC72 catalyst was used as cathode catalyst, and a 40 wt.% PtRu (1:1)/Vulcan XC72 was employed for the anode side. The CCM product is available at OMG under the designation "CCM-Type 7C" and was used with a 100 cm² (10 x 10 cm) of active area. The pas-

sive area (the non-coated area) of the CCM had a size of 1.0 cm in width, resulting in overall CCM dimensions of 12 x 12 cm with the active area centered in the middle.

Co-polyamide Vestamelt 3261 (Degussa, Düsseldorf) was provided as an extruded film of 120 μm thickness. From this film, two square-sized frames were punched with
5 inner dimensions of 9.8 x 9.8 cm and outer dimensions of 12 x 12 cm.

The catalyst-coated membrane was placed between the two frames of protective film, and the assembly was covered by two sheets of PTFE blanks. The protective film frames were positioned with respect to the catalyst-coated membrane so that the peripheral membrane rim was completely covered, and a 2 mm broad region of the active area was overlapping with the inner edge of the frame of protective film on both
10 sides of the CCM. Thus, the area of the overlapping region was 4 % of the total active area on both sides of the CCM. The region of the protective film overlapping with the non-coated membrane area was 100 % of the total non-coated membrane area on both sides of the CCM.

15 The package was placed between two graphite press plates and transferred into a press with a temperature of 165°C. Lamination was completed after 3 minutes at a pressure of 27 bar. The whole package was cooled down to room temperature while maintaining the pressure and then released from the press and disassembled. The frame of protective films around the active area adhered very well to both sides of the
20 CCM.

Subsequently, the catalyst-coated membrane and two gas diffusion layers (GDLs), one on the anode side and one on the cathode side, were mounted into a PEM single cell and tested in hydrogen/air operation at 2.7 bar operating pressure at 70°C cell temperature. The electrical performance was in the range of 650 mV at a current density of 600 mA/cm². During and after operation, no leakage of reactive gases was observed. Furthermore, the CCM with the protective film layers withstands frequent
25 assembly and disassembly processes without damage.

Example 2:

A catalyst-coated membrane (CCM) with protective film layers on both sides was
30 prepared according to the procedure described in example 1. Instead of the co-

polyamide material, a polyurethane-based film material (Walopur 4201AU, Epurex/Germany) with a thickness of 90 μm was used as the protective film layer. Lamination parameters were 27 bar and a temperature of 145°C for 2 minutes. The overlapping area of the protective film was about 5% of the total active area on both sides of the CCM. Furthermore, the overlapping area of the protective film with the non-coated area was about 100% of the total non-coated area. The catalyst-coated membrane and two GDLs were again mounted into a PEM single cell and tested in hydrogen/air operation at 1.0 bar / 70°C for an extended period of 300 hours. An excellent long-term performance was obtained. Microscopic inspection of the catalyst-coated membrane showed no indications for damage, either in the protective layers or at the interface between protective layer and active area of the CCM.

Example 3:

A catalyst-coated membrane (CCM) with protective films was prepared as described in example 2. The overlapping area of the protective films on both sides of the CCM was 5 % of the total active area. The overlapping area with the passive, non-coated membrane area was 100 %. Then the catalyst-coated membrane was placed between two GDLs (Sigracet 30BC from SGL Carbon, Germany) and the assembly was covered with two Teflon blanks. The GDLs were of the same size as the active area of the CCM (i.e. 100 cm²). The positioning of the gas diffusion layers was so that they completely covered the active area of the CCM and simultaneously overlapped with the protective film layer, which in turn overlapped with the active area of the CCM (see e.g., figure 2). Thus, the contacting/overlapping area of each GDL with the protective film layer was 5 % of the total GDL area.

The complete package was placed between two graphite press plates in a press with a temperature of 170°C. Lamination was completed after 3 minutes at a pressure of 25 bar. The whole package was cooled down to room temperature while maintaining the pressure and then released from the press and disassembled. The GDLs adhered well to the CCM thus forming a 5-layer membrane-electrode-assembly (MEA) with protective film layers on both sides.

The MEA was mounted into a PEMFC single cell and tested in hydrogen/air operation at 1.0 bar /70°C for 300 hours. A good long-term performance was obtained. Mi-

crossoscopic inspection of the 5-layer MEA showed no indications for damage, either in the protective layers or at the interface between the protective layers and the active area of the membrane-electrode-assembly.

5 Having thus described and exemplified the invention with a certain degree of particularity, it should be appreciated that the claims that follow are not to be so limited but are to be afforded a scope commensurate with the wording of each element of the claims and equivalents thereof.

30. Sep. 2002

Claims

1. A catalyst-coated membrane comprised of:
 - (a) an ionomer membrane, wherein said ionomer membrane comprises two surfaces and each of said two surfaces is comprised of:
 - 5 (i) an active area, wherein said active area is coated with a catalyst layer, and
 - (ii) a passive area; and
 - (b) at least one layer of protective film attached to each of the two surfaces of said catalyst-coated membrane, wherein said at least one layer of protective film overlaps the passive area and the active area.
- 10 2. The catalyst-coated membrane according to claim 1, wherein said passive area forms a perimeter around said active area.
3. The catalyst-coated membrane according to claim 1, wherein the region of the active area that is overlapped by the at least one layer of protective film is in the
15 range of 0.5 to 20 % of the total active area of the membrane, and the region of the passive area that is overlapped by the at least one layer of protective film is in the range of 80 to 150 % of the total passive area.
4. The catalyst-coated membrane according to claim 1, wherein the at least one layer of protective film comprises an organic polymer material with a thickness
20 in the range of 10 to 150 μm .
5. The catalyst-coated membrane according to claim 4, wherein the organic polymer material comprises a polymer selected from the group consisting of polytetrafluoroethylene, PVDF, polyethylene, polypropylene, polyester, polyamide, co-polyamide, polyamide elastomers, polyimide, polyurethane, polyurethane elastomers, silicones, silicon rubbers, and silicon based elastomers.
25
6. The catalyst-coated membrane according to claim 1, wherein the ionomer membrane comprises a substance selected from the group consisting of perfluorinated sulfonic acid polymers, acid-doped polybenzimidazoles, acid-group-

modified polyetherketones, ionically conductive organic/inorganic materials and composite reinforced materials.

- 5 7. A process for manufacturing a catalyst-coated membrane, said process comprising applying at least one layer of protective film to two surfaces of an ionomer membrane under pressure and heat for a period of 0.1 to 15 minutes, wherein said two surfaces each comprise a passive area and an active area, wherein said active area is coated with a catalyst layer.
- 10 8. A process for manufacturing a catalyst-coated membrane according to claim 7, wherein the pressure is in the range of 10 to 100 bar and the heat establishes a temperature in the range of 20 to 200°C.
- 15 9. A membrane-electrode-assembly comprised of:
- (a) an ionomer membrane, wherein said ionomer membrane comprises two surfaces and each of said two surfaces is comprised of:
 - (i) an active area, wherein said active area is coated with a catalyst layer, and
 - (ii) a passive area; and
 - (b) at least one gas diffusion layer, wherein said at least one gas diffusion layer covers the active area of said catalyst-coated membrane; and
 - (c) at least one layer of protective film, wherein said at least one layer of protective film contacts the active area, the passive area and the gas diffusion layer to form:
 - (i) an overlapped region of the active area,
 - (ii) an overlapped region of the passive area, and
 - (iii) an overlapped region of the gas diffusion layer.
- 20 10. The membrane-electrode-assembly according to claim 9, wherein the region of the active area contacted by the at least one layer of protective film is in the range of 0.5 to 20 % of the total active area of the membrane, the region of the passive area contacted by the at least one layer of protective film is in the range of 80 to 150 % of the total passive area of the membrane and the region of the
- 25

gas diffusion layer contacted by the at least one layer of protective film is in the range of 0.5 to 50 % of the total area of the gas diffusion layer.

- 5 11. A process for manufacturing a membrane-electrode-assembly, said process comprising applying a gas diffusion layer and at least one protective film to two surfaces of an ionomer membrane under pressure and heat for a period of 0.1 to 15 minutes, wherein said two surfaces each comprise a passive area and an active area, wherein said active area is coated with a catalyst layer.
- 10 12. A process for manufacturing a membrane-electrode-assembly according to claim 11, wherein the pressure is in the range of 10 to 100 bar and the heat establishes a temperature in the range of 20 to 200°C.
13. Use of catalyst-coated membranes according to claim 1 for manufacturing of PEM and DMFC fuel cell stacks.
14. Use of catalyst-coated membranes according to claim 8 for manufacturing of PEM and DMFC fuel cell stacks.

15

THIS PAGE BLANK (USPTO)

Abstract

The present invention relates to the field of electrochemical cells and fuel cells, and more specifically to polymer-electrolyte-membrane fuel cells (PEMFC) and direct methanol fuel cells (DMFC). It is directed to catalyst-coated ionomer membranes ("CCMs") and membrane-electrode-assemblies ("MEAs") that contain one or more protective film layers for protection, sealing and better handling purposes. The one or more protective film layers are attached to the surface of said catalyst-coated membranes in such a way that they overlap with a region of the passive non-coated ionomer area, and with a region of the active area that is coated with a catalyst layer. Furthermore, the present invention discloses a process for manufacture of CCMs and MEAs that contain protective film layers. The materials may be used as components for the manufacture of low temperature fuel cell stacks.

THIS PAGE BLANK (USPTO)

30. Sep. 2002




Figure 1




Figure 2

THIS PAGE BLANK (USPTO)